

Number #: 216-36B

Name: Majestic Grapefruit + Impact Velvet Silky Touch Blush

Category: Newsletters

Date: 02/25/2022



No	Phase	Trade Name	INCI	%
1	A	PureSyn 2	Hydrogenated Poly(C6-14 Olefin)	13.21
2	A	Floramac 10	Ethyl Macadamiate	26.20
3	A	Jeesilc PS-PTVL	Phenyl Trimethicone, Dimethicone/Vinyl Dimethicone Crosspolymer	3.54
4	A	Fancol ID-CG	Isododecane	4.78
5	A	Sansil-D308	Dimethicone (and) Dimethicone/ Vinyl Dimethicone Crosspolymer	1.98
6	B	Micropoly 250S	Polyethylene	5.30
7	B	Candelilla Wax	Euphorbia Cerifera (Candelilla) Wax	3.42
8	B	Synchrowax HR-C	Tribehenin	0.73
9	B	Microcrystalline Wax 180/185	Microcrystalline Wax	2.33
10	C	Majestic Pink Grapefruit	Mica (CI 77019), Red No. 30 Lake (CI 73360)	8.67
11	C	Impact Velvet	Mica	8.67
12	C	SanSil Pearl Resin	Polymethylsilsequioxane	5.00
13	C	SanSilica 610 AS	Silica, TES	5.81
14	C	SanTalc 511	Talc	5.00
15	D	Benzophenone-3	Benzophenone-3	2.72
16	D	Euxyl PE9010	Phenoxyethanol (and) Ethylhexylglycerin	1.32
17	D	Vitamin E	Tocopheryl Acetate	1.32
Total				100%
Procedure		Weigh all of phase A into glass beaker and heat to 90°C. Mix with propeller and continue mixing until all raws are dissolved and solution is homogenous. Mix phase B in a separate beaker at 95°C mix until all dissolved. Add phase B to A and continue mixing until uniform. Add C to AB while mixing with a homogenizer. Mix D in a separate beaker. Add phase D to the solution. Lower temperature to 70 °C. Pour into desired components.		

The information provided is furnished without warranty, expressed or implied, except that it is accurate to the best knowledge of Sandream Specialties LLC. Customers should utilize formulations provided as a guide and perform in-house stability, micro and other necessary testing.