

Number #: 216-85F

Name: Silikmira Xtreme TGPR Creme Eyeshadow

Category: Eye Makeup > Cream

Date: 11/10/2022

| No               | Phase | Trade Name                                                                                                                                                                                                                                                                                                             | INCI                                                 | %           |
|------------------|-------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------------------------------|-------------|
| 1                | A     | Floraester IPJ                                                                                                                                                                                                                                                                                                         | Isopropyl Jojobate (and) Jojoba Alcohol (and) Jojoba | 17.99       |
| 2                | A     | PureSyn 2                                                                                                                                                                                                                                                                                                              | Hydrogenated Poly(C6-14 Olefin)                      | 6.71        |
| 3                | A     | Floramac 10                                                                                                                                                                                                                                                                                                            | Ethyl Macadamiate                                    | 14.40       |
| 4                | A     | Permethyl 99                                                                                                                                                                                                                                                                                                           | Isododecane                                          | 5.00        |
| 5                | A     | Jeenate 2H                                                                                                                                                                                                                                                                                                             | Polyethylene                                         | 4.89        |
| 6                | A     | Jeenate 5H                                                                                                                                                                                                                                                                                                             | Polyethylene                                         | 4.00        |
| 7                | A     | SP 220                                                                                                                                                                                                                                                                                                                 | Cetyl Esters                                         | 2.45        |
| 8                | B     | Sansil 5012                                                                                                                                                                                                                                                                                                            | Mirasil C-DMX 12                                     | 12.86       |
| 9                | B     | Vitamin E                                                                                                                                                                                                                                                                                                              | Tocopheryl Acetate                                   | 0.20        |
| 10               | B     | Mica LL3                                                                                                                                                                                                                                                                                                               | Mica, Lauryl Lysine                                  | 5.00        |
| 11               | B     | HDK H30                                                                                                                                                                                                                                                                                                                | Hydrophobic Pyrogenic Silica                         | 0.50        |
| 12               | B     | SanSilica 610 AS                                                                                                                                                                                                                                                                                                       | Silica, TES                                          | 1.00        |
| 13               | C     | SilikMira Xtreme TGPR                                                                                                                                                                                                                                                                                                  | SiO2, TiO2, Aluminum, Synthetic Fluorophlogopite     | 25.00       |
| <b>Total</b>     |       |                                                                                                                                                                                                                                                                                                                        |                                                      | <b>100%</b> |
| <b>Procedure</b> |       | Weigh all of phase A into glass beaker and heat to 80°C. Mix with propeller and continue mixing until all raws are dissolved and solution is homogenous. Add phase B and slowly mix until uniform. Add phase C to A and B and rapidly mix until uniform. Pour into desired pots or vials and cool to room temperature. |                                                      |             |

The information provided is furnished without warranty, expressed or implied, except that it is accurate to the best knowledge of Sandream Specialties LLC. Customers should utilize formulations provided as a guide and perform in-house stability, micro and other necessary testing.